

Evaluation of Sorbed Polycyclic Aromatic Hydrocarbons on Biochar



Kurt Spokas

Research Soil Scientist USDA-ARS St. Paul, MN


















Introduction

- Polycyclic Aromatic Hydrocarbons (PAH)
 - Compose a large group of compounds (200+)
 - Characteristic of two or more fused <u>aromatic</u> carbon rings in the structure
 - Composed solely of <u>carbon and hydrogen</u> atoms
 - Simplest PAH is naphthalene











PAH Distribution

- PAHs are among the most common organic pollutants
 - Detected on every continent and virtually every location on the globe
- Universal presence
 - Universal presence
 - Ease of transport
 - Stability
- USEPA lists 32 of these PAHs as priority pollutants











PAH History

- Some PAHs are known human carcinogens
- Sir Percival Pott (1755)
 - Postulated that the high incidence of cancer in chimney sweeps was caused by an agent in chimney soot (later shown to be PAHs on soot)









PAH - Anthropogenic Sources



- Largest stationary point sources
 - Paper mills
 - Factories of consumer wood products
 - Petroleum refining













PAH Natural Sources

- Present in Fossil Fuels
 - Crude oil, coal, shale oils ...
- Present in gases (smoke) and ashes from
 - Forest /Prairie fires
 - Volcanoes



- Microbial degradation of black carbon
- Microbial production during humidification (complex SOM)











PAH Formation Processes

- Incomplete combustion
 - Burning fossil fuels
 - Biomass burning
 - Cooking for meal preparation



- PAH production also occurs:
 - Charcoal production
 - Present in bio-oil from biomass
 pyrolysis (e.g., Ré-Poppi and Santiago-Silva, 2002)

PAH Presence in Different Materials

Material	Σ USEPA PAH [μg g-1] ppm	Reference
Soils	th99 141	
Urban soil (roadside)	0.04 to 13.5	(Ritschel, 2008)
Arable soil (farmland)	0.2 to 0.4	(Ritschel, 2008)
Terrestrial rocks	<0.1 to 45	(Mahajan et al., 2001)
Other Biomass Materials:		
Pine Needles	0.04 – 1.9	(Ratola et al., 2010; Navarro-Ortega et al., 2011)
Wood Chips	0.01 to 0.015	(Chinnici et al., 2007)
Sewage sludge	2.2 to 126	(Wild et al., 1990; Ritschel, 2008)
Composts		
Wood chips/leaves/grass clippings	16.0	
Fall leaves/twigs	14.4	(Grossi et al. 2011)
Wood chips/sewage sludge	20.8	










Biochar: Name given to the production of black carbon for the purpose of soil carbon sequestration



▶ Biochar spans the entire spectrum of black carbon



PAH Presence in Black Carbons


	Σ USEPA PAH [μg g ⁻¹] ppm	Reference
Black Carbon Form	της ς 1 μριπ	
Coal	0.3 to 253	(Wang et al., 2010) (Laumann et al., 2011)
Slow Pyrolysis (wood)	<0.01	(Zhurinsh et al. 2005) (Singh et al., 2010)
Wood Ash (3.7% C content)	16.8	(Bundt et al., 2001)
Natural and synthetic charcoal	1.0 to 3.7	(Brown et al., 2006)
Coconut shell charcoal (CocoNara TM)	2.9	(Sepetdjian et al., 2010)
Hardwood Lump Charcoal	0.5	(Sepetdjian et al., 2010)
Three Kings TM (waterpipe charcoal)	1.2	(Sepetdjian et al., 2010)
Biochar (11 biochars/5 feedstocks)	<0.5	(Singh et al., 2010a)
Biochar (50 biochars) {Majority from same production unit}	0.3 to 45	(Hale et al 2012)

Current observed biochar range: 0.01 to 45 μ g g⁻¹

Biochars Examined

- ≈100 different biochars
- 50+ different pyrolysis units
 - Laboratory scale
 - Entrepreneur scale (homemade units)
 - Pilot scale
 - Small industrial scale units (tons/day)
 - Wood fired boilers (high C wood ash)
- Analyzed by multiple methods
 - Various solvent extraction/clean-up methods examined














Sum of total PAH range from 0.01 to 83 µg g⁻¹







- Highest sorbed PAH content: Slow Pyrolysis
 - Producer noted: Fire in the reactor that was extinguished with water during production/cooled



- ▶ MAP and Hydrothermal produced lower amount of PAH
 - ▶ Conditions not favorable for the production of PAH (?)
 - ▶ Some of these used sewage sludge (2 to 126 ppm)




Other studies – Hale et al. (2012)




Temperature Dependence

- PAH formation historically linked to higher production temperatures
 - Higher production temperatures lead to higher PAH levels



Temperature Dependence

- PAH formation
 historically linked to
 higher production
 temperatures
- However, there are exceptions
 - Not all pyrolysis units follow this trend



Factors in PAH formation

Not solely production temperature



- Original feedstock PAH levels ?
- Presence of <u>oxygen</u> is necessary to create PAH compounds
 - Presence of O₂ leads to increase PAH production

(Rey-Salgueiro et al., 2004)

- Moisture content of the feedstock
 - Dryer biomass producing lower PAH levels

(Bignal et al., 2008)

PAH Presence in Ashes

Material	Σ USEPA PAH [μg g ⁻¹] ppm	Reference
Bottom/fly ash mixture (wood feedstock)	37 – 77	(Davies et al., 1976; Dugenest et al., 1999; Johansson and van Bavel, 2003a)
Coal Fly Ash	15 – 185	(Gohda et al., 1993)
Municipal solid waste incinerator - bottom ash	0.5 to 3.6	(Johansson and van Bavel, 2003b)

• Incineration and gasification residues contain higher amounts of PAH compounds

 $(0.5 \text{ to } 185 \text{ µg g}^{-1})$

PAH Formation for Biochar


- Cooling biochars in oxygen (air) environment
 - Increases sorbed PAH content



- Moisture differences in the feedstock
 - Wetter feedstock leads to increased PAH levels



- Abiotic oxidation while sorbed to biochar
 - Time since production = important factor



Conclusions

- Sorbed PAH levels on biochar can be minimized through feedstock, pyrolysis, and storage conditions
- Production conditions are critical
 - <u>Exclusion of oxygen</u> is the most important, both during production AND cooling
 - Many sources air, water, carbohydrates, etc...
 - Biochar cooling avoid air (O₂) contact until cool
 - Use <u>dry feedstocks</u> to minimize PAH formation



Acknowledgements

- •Minnesota Department of Agriculture Specialty Block Grant Program
- •Minnesota Corn Growers Association

Dynamotive Energy Systems

Best Energies

Sylva Corp.

Northern Tilth

Avello Bioenergy

Acala Partners, LLC

Minnesota Biomass Exchange

NC Farm Center for Innovation and Sustainability

National Council for Air and Stream Improvement (NCASI)

Illinois Sustainable Technology Center (ISTC) [Univ. of Illinois]

Biochar Brokers

Chip Energy

AECOM

ICM, Inc.

Penn State

University of Bonn (Germany)

Laboratorio di Scienze Ambientali R.Sartori - C.I.R.S.A. (University of Bologna, Italy)

IRNAS-CSIC (Spain)

USDA-ARS Biochar and Pyrolysis Initiative (CHARnet)

Technical Support: Martin duSaire

Students:

Tia Phan, Lindsey Watson, Lianne Endo, Amanda Bidwell, Eric Nooker,

Kia Yang, Michael Ottman, Ed Colosky, Vang Yang, Tara Phan,

Abby Anderson, and Rena Weiss

